

# Magno™ gloss



Magno offers consistent high quality and reliability.

## PRODUCT INFORMATION

A superb gloss surface giving radiant colour intensity, sharp contrasts and extraordinary print detail.

- Consistent high quality and reliability
- Wide range of weights and sizes in sheets and reels available from UK and mill stocks
- FSC® Certified
- Available Carbon Captured

## PROCESS SUITABILITY

- Any suitable quality ink, suitable for dry toner

## TYPICAL USES

Ideal for:

- Direct contact with dry and fatty foodstuff

## STOCK SCHEDULE

● = Ream Wrap & Bulk Pack   ■ = Ream Wrap Only

| MM \ gsm   | 90 | 100 | 115 | 130 | 150 | 170 | 200 | 250 | 300 | 350 | 350 |
|------------|----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|
| 320 x 450  |    |     | ■   | ●   | ●   | ●   | ■   | ■   | ■   | ■   | ■   |
| 450 x 640  | ●  | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   |
| 520 x 720  | ●  | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   |
| 630 x 880  |    | ●   | ●   | ●   | ●   | ●   |     |     |     |     |     |
| 640 x 900  | ●  | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   |
| 720 x 1020 | ●  | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   | ●   |

N.B. A4 80gsm is available as Xpress Box, 2 hole punched and 4 hole punched

## SPECIFICATION

| Technical Information   |                    |      |      |      |      |      |      |      |      |      |      |      |
|-------------------------|--------------------|------|------|------|------|------|------|------|------|------|------|------|
|                         | g/m <sup>2</sup>   | 90   | 100  | 115  | 130  | 150  | 170  | 200  | 250  | 300  | 350  | 400  |
| BASIS WEIGHT            | g/m <sup>2</sup>   | 90   | 100  | 115  | 130  | 150  | 170  | 200  | 250  | 300  | 350  | 400  |
| THICKNESS               | µm                 | 64   | 72   | 83   | 91   | 107  | 124  | 148  | 185  | 228  | 273  | 320  |
| BULK                    | cm <sup>3</sup> /g | 0.71 | 0.72 | 0.72 | 0.70 | 0.71 | 0.73 | 0.74 | 0.74 | 0.76 | 0.78 | 0.80 |
| CIE WHITENESS (D65/10°) | %                  | 124  | 125  | 126  | 126  | 126  | 126  | 126  | 126  | 126  | 126  | 126  |
| GLOSS TAPPI 75°         | %                  | 66   | 66   | 66   | 66   | 66   | 66   | 66   | 68   | 68   | 68   | 68   |
| OPACITY                 | %                  | 90   | 92   | 93.5 | 94.5 | 96   | 97   | 98   | 98.5 | 99   | 99.5 | 99.5 |

Technical Information is given as an indication of typical values and is not to be considered as a commitment by the manufacturers.

The above information is given for general guidance only and is subject to change without notice.



[www.paper.co.uk](http://www.paper.co.uk)

Follow us

