
Scancote Elegance

Fully coated folding boxboard with single coated white back GC1. PEFC Certified.

BOARD PROFILE



Multiple blade coating

Bleached chemical pulp -> Bleached chemi-thermo-mechanical pulp (BCTMP) -> Bleached chemical pulp -> Single blade coating

PRODUCT INFORMATION

- The mill has ISO 9001 quality assurance scheme and ISO 14001 for environmental management.
- Scancote Elegance is made from 100% primary fibre from sustainable forests and is fully recyclable. PEFC 75%. (FSC available ex reels and mill makings).
- The bleached pulp used is elemental chlorine free (ECF).
- The high bulk of Scancote Elegance enables lighter weight boards to be used without reducing the required thickness, stiffness or opacity.
- Safe for direct contact with dry and non-fatty foods.
- Conforms to European standards regarding heavy metal content.
- This board is produced using virgin fibre, there is no recycled content.

PROCESS SUITABILITY

• Litho, Gravure, Screen printing, Letterpress, Flexo, UV and litho varnishing, Emulsion coating, Foil and film laminating, Embossing, Foil blocking

TYPICAL USES

- GRAPHIC Greeting cards, post cards, games cards, book and magazine covers, information cards, folders and wallets, point of sale promotions, CD and video sleeves.
- PACKAGING Cartons for healthcare, cosmetics, perfumes and food.

SPECIFICATION Sheet stock weights indicated*

	Microns	g/m2	Stiffness - Taber 15° mN.m	
			MD	CD
	210	170	2.9	1.4
	260	190	5.1	2.5
	305	210	8.0	3.8
	360*	235*	11.7	5.9
	400*	255*	16.2	8.1
	425	270	19.4	9.7
	450*	280*	21.4	10.7
	475	290	24.0	12.0
	500*	305*	26.8	13.4
	550*	330*	31.9	16.3
	600*	355*	37.4	19.2
	650*	380*	42.5	22.0
Tolerance	+/-3	+/-2	+/-15%	+/-15%
	Gloss		(Hunter 75°) 48% +/- 5 (PPS) 0.8m - 1.3m (top) (ISO) 91.5% +/- 1 (top)	
	Smoothness			
	Brightness			
	-		95% +/- 2 (back)	

The above information is given for general guidance only and is subject to change without notice.



www.paper.co.uk