
# White Peak GC2

Fully coated hard sized folding boxboard with cream back GC2. (FSC® Certified).

## **BOARD PROFILE**



Double blade coating

Bleached chemical pulp (ECF)

Bleached Thermo Mechanical Pulp and mill broke

Bleached chemical pulp/cream back (ECF)

# **PRODUCT INFORMATION**

- ISO 9000:2000 and ISO 14001 approved supplier.
- All pulp is sourced from well managed and sustainable forests and is fully recylable. (FSC<sup>®</sup> Mix Credit).
- The bleached pulp is ECF.
- Certified for safety with direct contact with dry and non fatty foods (ISEGA).
- Conforms to European standards regarding heavy metal content.
- Cobb Value Top (1 min) 25-45gsm, Back (2min) 50-80gsm.
- This board is produced using virgin fibre, there is no recycled content.

#### **PROCESS SUITABILITY**

- Litho
- Gravure
- Screen printing
- Letterpress
- Flexo
- UV and litho varnishing
- Emulsion coating
- Foil and film laminating
- Embossing
- Foil blocking
- Not guaranteed for reverse printing.

#### **TYPICAL USES**

- GRAPHIC Point of sale displays, CD and video sleeves.
- PACKAGING Cartons for cosmetics, health care and pharmaceuticals, frozen, chilled and other foods, drinks, toys and games and general cartons.

## SPECIFICATION Sheet stock weights indicated\*

	Microns	g/m2	Stiffness - Taber 15° mN.m		
			MD	CD	
	356*	215*	9.4	4.5	
	406*	235*	12.3	6.0	
	432*	250*	15.4	7.4	
	483*	260*	19.8	9.5	
	508*	275*	24.1	11.3	
	533*	295*	29.1	14.0	
	559	310	32.2	15.5	
	610*	325*	37.4	18.0	
	711*	370*	51.0	23.0	
Tolerance	+/-5%	+/-5%	-10%	-10%	
	Gloss		(Hunter 75°)	(Hunter 75°) >40	
	Smoothness		(PPS) 1.0µm	(PPS) 1.0µm +/- 0.5	
	Brightness		(ISO) 84% +/	(ISO) 84% +/- 2 (top)	
	Cobb Value Top (1 min) 25-45gsm, Back (2min) 50-80gsm.				

The above information is given for general guidance only and is subject to change without notice.



# www.paper.co.uk